

5042 EXPANDED NEOPRENE EPDM

<i>PROPERTIES</i>	<i>AVERAGE VALUE</i>
ASTM D1056	2A2
Density	112 kg/m ³
Compression Deflection 25%	35-63 kPa
Water Absorption	5%
Elongation %	180% min
Tensile Strength	700 Kg/m ²
FMVSS302	Pass
UL94 HF1	Pass
Temperature range	-56.6C to 93 C
Resistance	Excellent: Acid, Alkali, Oxidation, Ozone Good: Gasoline & Oil

The above figures are average values.

We recommend evaluation prior to use to ascertain the suitability of the material for the application.