

Versapor® R Membrane

Description

The Versapor R membrane is an acrylic copolymer membrane cast on a nonwoven nylon support. It is Repel™ treated for superior oleophobicity and hydrophobicity. The membrane is also available in a thinner version, on a nonwoven polyester support.

- Oleophobic/hydrophobic
- · Excellent air permeability
- Broad chemical compatibility
- · Compatible with a variety of sealing methods
- Excellent handling properties
- Manufacture is carried out according to procedures within a quality management system certified to ISO9001

The Versapor R membrane is repellent to a variety of fluids including, but not limited to, the following.

- Body fluids
- Lipid solutions
- Water
- Oils
- Organic solvents
- Gasoline
- Starter fluid
- Brake fluid
- Transmission fluid
- Steering fluid
- Wiper fluid

Specifications

Dimensions

Custom roll, sheet, and disc sizes available

Please contact your local Pall representative for more information.

Packaging

Core: 7.6 cm (3.0 in) ID, PVC

Packaging: For widths up to 22.86 cm (9.0 in), shrink-wrap around each roll; for widths 22.86 cm (9.0 in) and larger, bag around each roll



Versapor® R membrane

Qualification Services

Pall Corporation offers qualification services to support regulatory compliance.

Benefits of Venting

- Contamination control
- Controlled air/gas exchange rates
- Cost savings
- Design flexibility
- High permeability rates
- Higher throughput; increased fill rates
- Increased system reliability
- Parts remain free of corrosion
- Pressure equalization
- · Reactive surfaces are not poisoned
- Sensing surfaces protection
- Short circuits are prevented
- Temperature stabilization

Applications and Media Requirements by Industry¹

Automotive

Application

- ABS brake systems
- Air conditioning pressure sensors
- Electric motors: windows, windshield wipers
- Electronic control units
- Fuel tanks: pressure sensors, gas caps, roll-over valve protection
- · Lighting assemblies: headlight, taillight
- Powertrain control units

Media Requirements

- Easily die cut and sealed
- Good chemical resistance
- High mechanical strength
- High permeability
- High repellency to gasoline and other automotive fluids
- High vapor transport rate
- Low back pressure

Electronics

Application

- Acoustically transparent microphone protection
- Enclosure vents
- Micro-Electro-Mechanical Systems (MEMS) protection
- Portable electronic devices
- Transducer protectors
- Vented packaging

Media Requirements

- Easily die cut and sealed
- Good chemical resistance
- High acoustic transparency
- High water intrusion pressure
- Low back pressure
- · Resistant to salt water
- Resistant to UV
- Thin or low profile

Food and Beverage

Application

- Food packaging: processing, moisture protection, shipping
- · Liquid bottling: filling, packaging, shipping
- Thermal vents
- Vented cap and lid liners

Media Requirements

- Easily customized for unusual shapes
- Easily die cut and sealed
- Good chemical resistance
- Good mechanical strength
- Good repellency
- High permeability
- High temperature resistance

Other Industrial Applications²

- Cap and lid vents
- Moisture barriers
- Packaging vents
- Reactive product packaging
- Sensor protection

¹ This table is intended to serve as a guide only. Since applicable regulations and requirements may differ from country-to-country, please contact your local Pall representative for specific information.

² The Versapor R membrane is used in a variety of Industrial markets and applications. For information about those not listed above, please contact your local Pall representative.

Chemical Resistance^{3,4}

Acids

- Acetic acid 10%
- Acetic acid 30%
- Hydrochloric acid 1N (3.3%)

Alcohols

- Amyl alcohol
- Benzyl alcohol
- Butanol
- Ethanol
- Isopropanol
- Methanol
- n-Propanol

Aromatic Hydrocarbons

- Benzene
- Toluene
- Xylene

Bases

- Ammonium hydroxide 3N (5.7%)
- Ammonium hydroxide 6N (11.4%)
- Potassium hydroxide 3N (15%)
- Sodium hydroxide 3N (11%)
- Sodium hydroxide 6N (22%)

Esters

- Amyl acetate
- Butvl acetate
- Cellosolve acetate
- Ethyl acetate
- Isopropyl acetate

Ethers

- Ethyl ether
- Tetrahydrofuran/water (50/50 v/v): limited resistance
- Isopropyl ether

Glycols

- Ethylene glycol
- Glycerol
- Propylene glycol

Halogenated Hydrocarbons

- Carbon tetrachloride
- Ethylene dichloride
- Tetrachloroethylene
- Freon TF: limited resistance
- Genesoly D
- Perchloroethylene
- Trichloroethylene

Ketones

• Methyl isobutyl ketone

Miscellaneous

- 18 MOhm water
- Acetonitrile
- Formaldehyde 37%
- Formaldehyde 4%
- Gasoline
- Hexane dry
- JP-4
- Kerosene
- Pyridine: limited resistance
- Skydrol 500
- Water

Oils

- Cottonseed
- Peanut
- Sesame

Sealing Method Compatibility⁵

(Compatible)

Material							
	Adhesive Sealing	Heated Dies	Insert Molding	Mechanical Seal	Radio Frequency	Ultrasonic	
ABS	•	•	•	•	•	•	
Acrylic	•	•		•	•	<u> </u>	
EVA		•	•	•	•	•	
Latex	•			•			
Natural rubber	•			•	_		
Polycarbonate	•	•		•	•	•	
Polyester (PBT)	•	•		•	_	•	
Polyethylene		•	•	•			
Polypropylene		•	•	•	_	•	
PVC		•	•	•	•		
Silicone	•				_		
Styrene		•	•	•	_	•	
Synthetic rubber	•			•	_		
Urethane (thermoplastic)	•	•	•	•		•	

⁵ This table is intended to serve as a guide only. Accuracy cannot be guaranteed. Users should verify chemical compatibility with their specific membrane under actual conditions. Additional information about Pall materials is available online at www.pall.com/industrialmaterials.

³ The Versapor R membrane has demonstrated resistance to the chemicals on this list.

⁴ This table is intended to serve as a guide only. Accuracy cannot be guaranteed. Users are responsible for verifying chemical compatibility under their own conditions of use. Chemical compatibility is affected by many variables including temperature, pressure, concentration, and chemical purity.

Performance⁶

Part Number	Description	Rating (um)	Support Type	Suggested Maximum Operating Temp. C° (F°)	Oil Rating (1-8) ⁷	Minimum Thickness (mils)	Maximum Thickness (mils)	Water Intrusion psi (bar)	Air Flow Rate
80273	Versapor 200R	0.2	Nonwoven nylon	150 (302)	8	6.0	12.0	≥ 26.0 (1.79)	≥ 4.78
80274	Versapor 450R	0.45	Nonwoven nylon	150 (302)	8	6.0	12.0	≥ 16.0 (1.10)	≥ 16.68
80275	Versapor 800R	0.8	Nonwoven nylon	150 (302)	8	6.0	12.0	≥ 8.0 (0.55)	≥ 43.58
80276	Versapor 1200R	1.2	Nonwoven nylon	150 (302)	8	6.0	12.0	≥ 6.0 (0.41)	≥ 37.89
80256	Versapor 3000R	3.0	Nonwoven nylon	150 (302)	8	6.0	12.0	≥ 3.0 (0.21)	≥ 60.0 ⁹
80277	Versapor 5000R	5.0	Nonwoven nylon	150 (302)	8	6.0	12.0	≥ 2.0 (0.14)	≥ 88 ⁹
80278	Versapor 10000R	10.0	Nonwoven nylon	150 (302)	8	6.0	12.0	≥ 0.5 (0.03)	≥ 113.0 ⁹

⁶ The maximum operating temperatures listed are guidelines only. Accuracy cannot be guaranteed. Users should verify maximum temperature during continuous operation under actual conditions.

Ordering Information

For ordering information, or to place an order, please contact your local Pall representative.



Industrial Materials

25 Harbor Park Drive Port Washington, NY 11050 +1 516 484 3600 phone +1 516 625 3610 fax

Pall Trincor
Pall Membrane Technology Center
770 Pennsylvania Drive, Suite 100
Exton, Pennsylvania 19341
+1 610 458 9500 phone
+1 610 458 9595 fax

Pall Filtersystems GmbH Werk Schumacher Crailsheim Zur Fluegelau 70 D 74564 Crailsheim +49 7951 3020 phone +49 7951 26511 fax Nihon Pall Ltd. 6-8-1, Nishishinjuku Shinjuku-Ku Tokyo, Japan, 163-6017 +81 3 6901 5800 phone +81 3 5322 2134 fax

Visit us on the Web at www.pall.com/industrialmaterials

Pall Corporation has offices and plants throughout the world. For Pall representatives in your area, please go to www.pall.com/contact.

Because of technological developments related to the products, systems, and/or services described herein, the data and procedures are subject to change without notice. Please consult your Pall representative or visit www.pall.com to verify that this information remains valid.

© Copyright 2010, 2009, Pall Corporation. Pall, (PALL), and Versapor are trademarks of Pall Corporation. ® Indicates a trademark registered in the USA.

Filtration. Separation. Solution.sm is a service mark of Pall Corporation.

⁷ Hydrocarbon resistance test was performed according to AATCC Test Method 118-1989.

⁸ Air flow rate units: Lpm / 3.7 cm² @ 13.5 psi (0.9 bar)

 $^{^{9}}$ Air flow rate units: Lpm / 3.7 cm 2 @ 5.0 psi (0.34 bar)