

PORON Medical® Urethanes

**PORON Medical® Urethanes – Soft – Cushioning & Soft – Supporting
Typical Physical Properties**

PROPERTY	TEST METHOD	PRODUCT	
Formulation		PORON Medical (Soft - Cushioning)	PORON Medical (Soft - Supporting)
*Density, kg/m ³ (lb. / ft ³)	ASTM D 3574-95 Test A	240 (15)	320 (20)
Specific Gravity		0.24	0.32
Tolerance, %		± 10	
*Standard Thickness		See Product Availability	
Tolerance, %		± 10	
Standard Colors (Code)		Neutral (05) Aquamarine (72)	Beige (40) Light Blue (14)
Air Permeability	Gurley Densometer	Open-Cell – Breathable	
*Compression Set, % max.	ASTM D 3574 Test D @ 70°C (158°F)	10	
Compression Force Deflection, kPa, (psi)	0.2"/min. Strain Rate Force Measured @ 25% Deflection	27 – 55 (4 – 8)	41 – 97 (6 – 14)
Hydrolysis Resistance, Compression Set, % Max	ASTM D 3574 Test J / Test D after autoclaved 5 hrs @ 121°C (250°F)	Good Resistance 5	
Resilience, Shore Instrument Resiliometer, avg (Ball Rebound Tester)	ASTM D 2632-96, Vertical Rebound	24	25
Water Vapor Transfer, Typical g/m ² /24hrs (G/ft ² /24hrs)	Based on ASTM E 96-00	200 (19)	
Water Absorption, Typical % Wt Gain	Based on ASTM D 570	< 20	
Antimicrobial, Fungal Resistance	ASTM G21	Does not promote fungal growth	
Skin Contact Primary Skin Irritation	ISO 10993-10, 2010	Pass	
Tear Strength, kN/m (pli, min.)	ASTM D 624 Die C	0.5 (3)	0.9 (5)
*Tensile Elongation, % min.	ASTM D 3574 Test E	100	
*Tensile Strength, kPa (psi, min.)	ASTM D 3574 Test E	276 (40)	448 (65)
Temperature Resistance, max Recommended Constant Use Recommended Intermittent Use	ASTM D 746-98	90°C (194°F) 121°C (250°F)	
Chemical Resistance		PORON® Urethanes are unaffected by mild organic acids and bases. They show modest swelling with oils and greases and other linear hydrocarbons. Strongly polar solvents will greatly swell PORON Urethanes. In most cases, physical properties recover to a great extent as the solvents evaporate.	

Notes:

1. Typical values are a representation of an average value for the population of the property. For specification values, contact Rogers Corporation.
2. All metric conversions are approximate.
3. Additional technical services are available.

The information contained in this data sheet is intended to assist you in designing with Rogers PORON Medical Urethanes. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers PORON Medical Urethanes for each application. The Rogers logo, The world runs better with Rogers., PORON and PORON Medical are licensed trademarks of Rogers Corporation. © 2003, 2005, 2013, 2015 Rogers Corporation, All rights reserved. Printed in U.S.A. 0315-PDF, Publication #10-017